



Oriental Trexim Pvt. Ltd.

Building Future

ORISIL Micro-White Microsilica / Silica Fume

CONCRETE

Analysis/Properties		Limits	
SiO ₂	Silicon Dioxide, Amorphous	min	90%
CaO	Calcium Oxide	max	0.30%
Fe ₂ O ₃	Iron Oxide	max	0.5%
Al ₂ O ₃	Aluminium Oxide	max	5.0%
ZrO ₂	Zircon	max	1.2%
MgO	Magnesium Oxide	max	0.1%
K ₂ O	Potassium Oxide	max	0.1%
Na ₂ O	Sodium Oxide	max	0.5%
H ₂ O	Moisture, as packed	max	1.0%

Mehods for Microsilica. The above ORISIL Microsilica specification refers to analysis performed using the ASTM Standard Test

ORISIL Microsilica® is a registered trademark and belongs to Oriental Trexim Pvt. Ltd

Oriental Trexim Pvt. Ltd

Tel: +91 22 27802935 Fax: +91 22 27895783

E-mail: orientaltrexim@gmail.com [Http://www.orientaltrexim.com](http://www.orientaltrexim.com)

Add: 521, Grohitam Bldg, Plot No : 14B, Sector 19, Vashi, Navi Mumbai - 400705 INDIA